

## IN THE CLAIMS

1. (Currently Amended) A nonwoven ~~Nonwoven~~ layer for a filter, in particular, for a vacuum cleaner bag, wherein the non-woven layer comprising at least one region of the ~~nonwoven layer, the region having a predetermined thickness and a predetermined area, has~~ having a surface area smaller than the filter and having an average pore size smaller than 50  $\mu\text{m}$ , ~~and comprises the at least one region comprising~~ fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the layer region is inhibited, ~~the nonwoven layer is a spunbond nonwoven layer, wherein the at least one region is a hot calendered region, and wherein the nonwoven layer is a spunbond nonwoven layer.~~

2. Cancelled.

3. (Previously Presented) The nonwoven ~~Nonwoven~~ layer according to claim 1, having a basis weight between 10 and 100  $\text{g/m}^2$  and wherein the spunbond fibers have an average fineness of 0.6-12 denier.

4. (Currently Amended) The nonwoven ~~Nonwoven~~ layer for a filter, in particular, for a vacuum cleaner bag, wherein the non-woven layer comprising at least one region of the ~~nonwoven layer, the region having a predetermined thickness and a predetermined area, has~~ having a surface area smaller than the filter and having an average pore size smaller than 50  $\mu\text{m}$ , ~~and comprises the at least one region comprising~~ fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the layer region is inhibited, ~~the nonwoven layer is a spunbond nonwoven layer, wherein the at least one region comprises an adhesive and wherein the nonwoven layer is a spunbond nonwoven layer.~~

5. (Currently Amended) The nonwoven ~~Nonwoven~~ layer according to claim 4, wherein the adhesive is a hotmelt, a cold glue, a dry-bond adhesive, a thermoplastic polymer, or

mixtures thereof.

6. (Currently Amended) The nonwoven ~~Nonwoven~~ layer according to claim 5, wherein the amount of hotmelt is between 1 and 10 g/m<sup>2</sup>.

7. Cancelled.

8. (Currently Amended) A composite ~~Composite~~ layer for a filter, ~~in particular,~~ for a vacuum cleaner bag, comprising:

a first nonwoven layer according to claim 3, and

a second nonwoven layer on top of the first nonwoven layer,

wherein an adhesive is located at an interface between the first and second nonwoven layer such that fibers of the first or the second nonwoven layer or the first and the second nonwoven layer are bonded together and a movement of the fibers in the first or second nonwoven layer or the first and second nonwoven layer relative to each other in a direction parallel to a surface of the first layer or the second layer is inhibited.

9. (Currently Amended) The composite ~~Composite~~ layer according to claim 8, wherein the second nonwoven layer is a meltblown nonwoven layer, and wherein the adhesive is a hotmelt.

10. Cancelled.

11. (Currently Amended) A method ~~Method~~ for producing a nonwoven layer for a filter wherein the nonwoven layer is a spunbond nonwoven layer and at least one region of the nonwoven layer, ~~the region having a predetermined thickness and a predetermined area,~~ has an average pore size smaller than 50 µm and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the layer ~~region~~ is inhibited, the method comprising the steps of:

treating at least one region of the nonwoven layer, the treated region having a smaller surface area than the filter~~the region having a predetermined thickness and a predetermined area~~, such that the ~~nonwoven layer~~ treated region has an average pore size smaller than 50  $\mu\text{m}$  and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the ~~layer~~ region is inhibited, wherein the treating step comprises the steps of:

spraying of hotmelt, cold glue, dry-bond adhesive, thermoplastic polymer, or mixtures thereof, and

applying pressure to obtain a bonding of the fibers in the treated region.

12. (Currently Amended) A method ~~Method~~ for producing a nonwoven layer for a filter wherein the nonwoven layer is a spunbond nonwoven layer and at least one region of the nonwoven layer, ~~the region having a predetermined thickness and a predetermined area~~, has an average pore size smaller than 50  $\mu\text{m}$  and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the ~~layer~~ region is inhibited, the method comprising the step of:

treating at least one region of the nonwoven layer, the treated region having a smaller surface area than the filter~~the region having a predetermined thickness and a predetermined area~~, such that the ~~nonwoven layer~~ treated region has an average pore size smaller than 50  $\mu\text{m}$  and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the ~~layer~~ region is inhibited, wherein the treating step comprises the step of hot calendering.

13. (Currently Amended) A method ~~Method~~ for producing a composite layer according to claim 8 comprising the steps of:

providing a first nonwoven layer,

applying an adhesive to the first nonwoven layer, and

providing a second nonwoven layer,

wherein an adhesive is located at an interface between the first and second nonwoven layer such that fibers of the first or the second nonwoven layer or the first

and the second nonwoven layer are bonded together and a movement of the fibers in the first or second nonwoven layer or the first and the second nonwoven layer relative to each other in a direction parallel to the surface of the layer is inhibited.

14. (Currently Amended) The method ~~Method~~ according to claim 13, further comprising the step of applying pressure to obtain a bonding of the fibers.

15. (Currently Amended) A filter ~~Filter medium, in particular,~~ for a vacuum cleaner bag, comprising a filter structure ~~characterized in that~~ comprising a surface or an interface of the filter structure is provided with a filter paper layer defining a first region having a smaller surface area than the filter structure, the filter paper layer at the first region having reduced air permeability relative to a second region of the filter structure free of the filter paper layer.

16. (Currently Amended) The filter ~~Filter medium~~ according to claim 15, wherein the filter paper layer is bonded to the filter structure.

17. (Currently Amended) The filter ~~Filter medium~~ according to claim 16, wherein the filter paper layer is bonded using an adhesive wherein the adhesive is a hotmelt, a cold glue, a dry-bond adhesive, a thermoplastic polymer or mixtures thereof.

18. (Currently Amended) The filter ~~Filter medium~~ according to claim 16, wherein the filter paper layer is bonded to the filter structure at discrete region.

19. (Currently Amended) The filter ~~Filter medium~~ according to claim 15, wherein the filter structure comprises a nonwoven layer.

20. (Currently Amended) The filter ~~Filter medium~~ according to one of the claim 15, wherein the filter structure comprises successively a spunbond, an air-laid, a spunbond, a melt-blown, and a spunbond layer.

21. (Currently Amended) The filter ~~Filter~~ medium according to claim 15, wherein the filter paper layer has an air permeability of at least about 250 l/m<sup>2</sup>/s.

22. (Currently Amended) A vacuum ~~Vacuum~~ cleaner bag comprising a filter medium, the filter medium comprising a filter structure wherein a surface or an interface of the filter structure is provided with a filter paper layer defining a first region having a smaller surface area than the filter structure, the filter paper layer at the first region having reduced air permeability relative to a second region of the filter structure free of the filter paper layer.

23. (Currently Amended) The vacuum ~~Vacuum~~ cleaner bag according to claim 22, wherein the filter paper layer is provided at a region of a surface of the filter structure such that, in operation, the region is exposed directly to an airflow entering the bag.

24. (Currently Amended) The vacuum ~~Vacuum~~ cleaner bag according to claim 22 comprising two portions of filter medium wherein both portions are bonded together at an outer edge and wherein the first portion comprises an air inlet and the second portion comprises the filter paper layer at a region opposite to the air inlet.

25. (Currently Amended) The vacuum ~~Vacuum~~ cleaner bag according to claim 22, wherein the filter paper layer is provided at the inner surface or the outer surface of the bag.

26. (Currently Amended) The nonwoven ~~Nonwoven~~ layer according to claim 4, wherein the adhesive is a pulverized polymer.

27. (Previously Presented) The method according to claim 11 wherein the polymer comprises a pulverized polymer.

28. (Currently Amended) The filter ~~Filter~~ medium according to claim 15, wherein the filter paper layer has an air permeability of at least about 500 l/m<sup>2</sup>/s.

29. (Currently Amended) The filter ~~Filter~~ medium according to claim 15, wherein the filter paper layer has an air permeability of at least about 600 l/m<sup>2</sup>/s.